

Champion Seat Floor Mount

Chart A

Property	Aisle Standard No Break Polypropylene	Seat and Back Solid Injection Molded No Break Polypropylene
Tensile Strength	2,600 lbs	4,600 lbs
Flexural Strength	3,000 lbs	—
Flexural Modulus	80,000 lbs	200,000 lbs
Hardness,	M101	M85/R115
IZOD Notched Impact	No Break	3
Heat Deflection Temp (° F/° C) at	125/52	—
Melting Temperature	320/160	320/160
Flammability Rating	HB	N.R
Max Operating Temp (° F/° C)	180/82	180/82

Other widths available depending upon quantity.

